




It's been a few years since I've been able to work with blackgum. The heartwood is darker (with a consistent color) then the sapwood and tends to separate from itself upon drying. It has a tight grain pattern and takes to finish well. The project photo is a wine goblet made with heartwood with sandstone inlay.



| | | |
|--|---|--|
| <div>7/4/2010 2:58:41 PM</div>  | <div>7/4/2010 3:00:21 PM</div>  | <div>7/4/2010 2:59:52 PM</div>  |
| Radial | Tangential | Transverse |